



## ZeroStat DuroSeal Rubber Coat

DuroSeal is a water-based urethane/acrylic polymer formulation for poured or sheet urethane, rubber, or polyvinyl chloride (PVC) sport flooring surfaces. DuroSeal offers exceptional adhesion and durability while maintaining the high degree of flexibility required to conform to the variable surface conditions of Sport Flooring materials. This flexibility helps avoid the problems of fracturing and cracking associated with some types of finishes used on these synthetic floors. DuroSeal is easily maintained with ZS-Tops Synthetic Neutral Cleaner for routine soil conditions or ZeroStat Super Blue for heavier soil, and can be removed with ZS-Eliminator stripper.

### APPLICATION & MAINTENANCE

**For initial application** remove any existing finish with Eliminator. Scrub the floor surfaces with a deep cleaning pad (green or blue), or a good quality nylon brush for textured surfaces. Vacuum or mop up the scrubbing solution and rinse the floor with clean water. Optimum results are obtained by applying two or three thin coats of DuroSeal, allowing at least one hour drying time between coats.

**For irregular surfaces** dilute the finish with equal amounts of water and apply a light coat with a pressurized or airless sprayer. **Regular maintenance** will extend the life of DuroSeal. Sweep, or dry mop with a mop treated with Aqua Treat water-based mop treatment at least daily or more often as necessary. Follow by damp mopping with Tops Neutral Cleaner, or Stand Up. Avoid using harsh cleaners and oil-based mop treatments. Do not use high speed burnishing machines on these types of flooring.

### SPECIFICATIONS:

Nonvolatile Solids	12 - 13%
Total Active	15 + 0.5%
pH	8.0 + 0.5
Gloss	80+
Color	Light Green
Weight Per Gallon	8.4
Slip Resistance (ASTM)	Exceeds 0.5
Stability	1 year minimum at room temperature
Freeze/Thaw Stability	3 cycles minimum
Drying Time	20 minutes
Water Resistance	Excellent
Coverage	1000-1500 Ft.
Removability (Gardner)	70 maximum

### SAFETY INFORMATION:

Health	1
Flammability	0
Reactivity	0
Personal Protection	B

This material is not a hazardous mixture, as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. For detailed information consult MSDS sheet.

ITEM	DESCRIPTION	SIZE
ZS-DuroSeal-G	ZS-DuroSeal Rubber Coat	1 gallon
ZS-DuroSeal-5	ZS-DuroSeal Rubber Coat	5 gallon

## ZEROSTAT DUROSEAL RUBBER COAT

PRODUCT  
ZEROSTAT DUROSEAL RUBBER COAT

ITEM NUMBER  
ZS-DUROSEAL

DATA SHEET  
#1000



1-877-GND-ZERO (463-9376)  
 FAX: 941-751-7586  
 4916 26<sup>TH</sup> Street West #100  
 Bradenton, Florida 34207  
 EMAIL: sales@gndzero.com  
 www.gndzero.com