

ZeroStat Coat-XL

Static Dissipating Floor Finish

Static dissipating, metal free, aqueous co-polymer floor finish

Detergent, salt and slip resistant

Easily applied, excellent wear properties, high gloss

PRODUCT DESCRIPTION

ZeroStat Coat-XL, a state-of-the-art floor maintenance finish with inherent static-dissipating properties, is specifically formulated for application in computer rooms, electronic assembly areas, telephone substations, or any other area where positive elimination of static electricity is a prime consideration. Its unique static dissipating ingredient is actively linked to the chemical structure of the polymer system, preventing washout or leaching of the static dissipating properties. Easy maintenance, good gloss, and durability are additional assets of this high-tech antistatic finish.

APPLICATION & MAINTENANCE

NOTE: All previous versions of ZeroStat Coat or other Anti-Static Floor Finishes must be removed with ZeroStat Eliminator Finish Stripper prior to the application of ZeroStat Coat-XL.

Floor surfaces should be 60o F or warmer and in relative humidity conditions between 40-60%. Remove old finish with ZeroStat Eliminator. Follow directions on stripper label for application. To obtain static dissipative properties on regular vinyl composition tile, a minimum of three to five coats are required. 2 coats of ZeroStat Coat-XL are recommended for static dissipative or conductive tiles. Apply thin even coats, allowing 1 to 2 hours between coats depending on humidity conditions. No more than 3 coats should be applied in a 24-hour period. Recoating of existing finish: Sweep the floor to remove any loose dirt or dust. Wash the floor with ZeroStat Clean-XL to remove dirt and soil. Apply thin even coats, allowing 1 to 2 hours between coats depending on humidity conditions. The frequency of refinishing will vary depending on the efficacy of the maintenance program and environmental conditions.

Routine maintenance: Floor surfaces should be swept with an untreated mop daily. ZeroStat Coat-XL should be damp mopped only with ZeroStat Clean-XL regularly, to remove soil, salt, and film deposits which can degrade the coatings static dissipative properties and gloss. Spray buffing or high speed burnishing with a soft polishing pad and ZeroStat Buff-XL is recommended to maintain optimum appearance and static dissipating properties. Do not buff or burnish any sooner than 5 days after the last coat of ZeroStat Clean-XL is applied.

For optimum results do not apply during excessively humid conditions (>60% RH) and do not dry buff or dry burnish.

SAFETY INFORMATION

Health	1
Flammability	0
Reactivity	0
Personal Protection	B

This material is not a hazardous mixture as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. If ingested, drink one or two cups of milk or water. In the event of eye contact, flush area with water for 15 minutes. **Contact a Physician.** For detailed information, consult MSDS sheet.

SPECIFICATIONS

Nonvolatile Solids	22 ± 0.6%
Total Active	25%
Resistivity-ASTM D257	10 ⁸ Ohms ² Max/Cm ² @ 40% Relative Humidity
Static Dissipation	0.02 Second
pH	7.4 - 8.0
Gloss 60 ⁰	80+ @ 3 Coats
Color	Blue Green
Weight Per Gallon	8.4 - 8.6
Slip Resistance (ASTM)	0.52 minimum
Stability	1 year minimum at room temperature
Freeze/Thaw Stability	3 cycles minimum
Drying Time	1-2 Hours
Water Resistance	Good
Gallon Coverage (Feet ²)	1500 - 2000 ft ²
Removability (Gardner)	75 cycles maximum

Product No.

27



P.O. BOX 70
Bradenton, Florida 34206
Toll Free: 877-463-1376
Direct Phone: 941-751-7581