



# Ground Zero Electrostatics THERMOFORMED PLASTIC

## Thermoformed Plastic

PROPERTY	TEST METHOD	VALUE
Surface Resistivity	EOS/ESD S11.11-1993	< 1.0X10 <sup>9</sup>
Static Decay Rate	mil.-B-81705C & EIA-541	< 2.0 seconds

### TYPICAL PHYSICAL PROPERTIES

PROPERTY	ASTM TEST METHOD	UNITS	VALUE
<b>GENERAL</b>			
Specific Gravity Light	D792		1.33
Transmission	D1003	% @ .010" thickness	80.5
Haze	D1003	% @ .010" thickness	.5
<b>MECHANICAL</b>			
Tensile	D638	psi	6,700
Tensile Modulus	D638	psi	350,000
Flexural Strength	D790	psi	12,200
Rockwell Hardness	D785	"R" scale	102
Izod Impact	D256	ft. lb./in. of 1/8" notch	19
Heat Deflection@ 64psi	D648	bar C°	61

### CHARACTERISTICS

- Excellent clarity for immediate product recognition and bar code scanning
- Low outgassing
- Does not generate particulate
- Not humidity dependent
- Provides packaging design flexibility
- Extremely low corrosion potential
- Controlled elimination of static charges
- Continuous dissipation
- No "sloughing" or scratch transfer
- Washable/reusable

*All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Ground Zero Electrostatics. as to the effects of such use or the results to be obtained, nor does Ground Zero Electrostatics. assume any liability arising out of use, by others, of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable, when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.*

