



Ground Zero Electrostatics Polyurethane Foam Specifications

Conductive Polyurethane Foam Specifications

PHYSICAL PROPERTY	TEST METHOD	REQUIREMENTS
COLOR	N/A	Slate, Blue
DENSITY (#/CU.FT)	ASTM D-3574-91	1.60-1.70
25% IFD	ASTM D-3574-91	91-105
PERMEABILITY	N/A	40 – 60%
TENSILE STRENGTH	ASTM D-3574-91	25 PSI Min.
ELONGATION	ASTM D-3574-91	150% Min.
TEAR RESISTANCE	ASTM D-3574-91	1.25 PPI Min.
RESILIENCE TEST	ASTM D-3574-91	25% Min.
COMPRESSION SET @ 90% COMPRESSION	ASTM D-3574-91	10% Max
CAL-117 FLAMMABILITY	CA Bureau of Home Furn bulletin #117	N/A
BLOWING AGENT	N/A	CFC Free



4916 26th Street West, Suite 100, Bradenton, Florida 34207

Toll Free 877-GND-ZERO (463-1376), **Direct Phone** 941-751-7581 **Fax** 1-941-751-7586

Email sales@gndzero.com

http://www.gndzero.com